

UNCLASSIFIED

AD NUMBER
AD851844
NEW LIMITATION CHANGE
TO Approved for public release, distribution unlimited
FROM Distribution authorized to U.S. Gov't. agencies only; Administrative/Operational Use; 22 APR 1969. Other requests shall be referred to Army Foreign Science and Technology Center, Washington, DC 20315.
AUTHORITY
USAFSTC ltr 4 Aug 1969

THIS PAGE IS UNCLASSIFIED

U.S. ARMY FOREIGN SCIENCE AND TECHNOLOGY CENTER

AD851844



ALTERATIONS IN MAIZE STARCH UNDER THE ACTION
OF IRRADIATION AND TEMPERATURE

COUNTRY: USSR

TECHNICAL TRANSLATION

The translation rights of this document have not been obtained. This document is not in the public domain.

Each transmittal of this document outside the agencies of the U.S. Government must have prior approval of the U.S. Army Foreign Science and Technology Center.

WASH DC 20315

DDC
RECEIVED
MAY 13 1969
C

TECHNICAL TRANSLATION

FSTC-HT-23-745-68

**ALTERATIONS IN MAIZE STARCH UNDER THE ACTION
OF IRRADIATION AND TEMPERATURE**

V.A. Yakovenko, N.V. Romenskiy and L.V. Masenko
(Odessa Technological Institute imeni M.V. Lomonosov)

Source: IZVESTIYA VYSSHIKH ZAVEDENIY PISHCHEVAYA TEKHNLOGIYA
(Information of Higher Schools Food Technology)
pp. 42-44. Russian

Translated for FSTC by Techtran Corporation

This translation is a rendition of the original foreign text without any analytical or editorial comment. Statements or theories advocated or implied are those of the source and do not necessarily reflect the position or opinion of the US Army Foreign Science and Technology Center. This translation is published with a minimum of copy editing and graphics preparation in order to expedite the dissemination of information. Requests for additional copies of this document should be addressed to the Defense Documentation Center, Cameron Station, Alexandria, Virginia, ATTN: OSR-2

ALTERATIONS IN MAIZE STARCH UNDER THE ACTION OF IRRADIATION AND TEMPERATURE

The action of ionization of irradiational starch causes a rupture of the 1-4 and 1-6 leukocyte bonds and leads to the depolymerization of the molecules and the degradative cleavage of functional grooves [1-4]. It was assumed, [2,5] that in addition to the degradation of the micromolecules that "cross-linking" also takes place.

The study starts from the maize VIR-42 which was dried at temperature of the heat carrier of $T = 140^{\circ} \text{C}$. (The moisture content of the corn prior to drying was 19% and after drying it was 8%). A standard method was used to determine the germination and energy of sprouting in the irradiated dried corn and in the original corn.

Completely ripe corn containing 13% moisture was irradiated with gamma rays of Co60 using a GUB-800 unit and exposure doses of 10^5 and $1.5 \cdot 10^6 \text{R}$. Then the method described in [6] was used to extract the starch also from the non-irradiated corn.

The ratio of the viscosity was calculated from the mean arithmetic values of the discharge time of a starch solution of different concentration in NaOH and a solution of NaOH using a Pinkevich viscometer with a capillary 0.73 mm in diameter at 20°C . The molecular weight in the degree of polymerization would be determined by the method of terminal groups in accordance with a Gagedorn-Jensen [7] method. The alkali lability was determined by the Schoch and Jensen Method [8]. The Amylose content was determined by the "blue number" method as developed by Smirnova-Ikonnikova [9].

As can be seen from Table 1, for doses of 10^5 and $1.5 \cdot 10^5$ are, the energy of sprouting decreases while at $1.5 \cdot 10^6$, the germination also decreases.

Table 1

Conditions for Treating Fully Ripe Corn	Energy of Sprouting	Germination	Starch Yield	Content of Crude Protein therein	Ratio of Viscosities for Starch Content				Degree of Polymerization	Molecular Weight	Amylose Content	Alkali Lability
					Weight Mean %							
					2	1	0.5	0.25				
Without Treatment Irradiation. R 10 ⁵ 1.5-10 ⁶ Drying at 140°C	97	100	57.7	0.65	54.1	6.1	2.3	1.6	710	115000	14.5	18.0
	87	100	56.8	0.65	41.7	4.06	2.2	1.39	544	88070	14.5	18.3
	85	91	58.0	0.63	4.6	2.19	1.47	1.24	299	48500	14.0	22.9
	0	0	42.4	1.64	30.7	5.6	2.1	1.39	132	70000	15.0	16.4

The effect of irradiation on a starch yield and the content of "crude" protein, was not observed. The ratio of the viscosities, and the molecular weight decreased even for a small dose, and the alkali lability increases, and the Amylose content, does not change. Starch from corn dried at 140° C shows an increased content of "crude" protein. It has been possible to reduce it to 1.06%, and in the control to 0.34% after purification of the starch with ethyl alcohol [10].

Then we obtained solutions of starches of 0.1% concentration by dispersing the starch samples for 2 and 24 hours in 1 n NaOH.

These were filtered and then studied on an SF-4A spectrophotometer and the square cell would be the side of the square equal to 10 mm and within wave-length range of 230--610 NM.

The optical density D of the solution of irradiated starch was much lower than that of the control. A decrease in the molecular weight and D, as well as an increase in the alkali lability, indicate that even for small doses of irradiation, ruptures of the intramolecular forms of the starch are possible. The optical density of the solution of starch obtained from dried corn after purification with alcohol decreases. The solutions of unpurified starch from the same corn give a much higher D in comparison with the control. Apparently, during the drying the protein reacts with the starch as the result of which the separation with alcohol is hindered and this affects the change of the absorption spectra. By comparing the letter in the case of the starches and the Amyloses under study, which were obtained from the control and the dried grain in accordance with the Schoch Method [11] (Table 2), it can be assumed that under the action of a high T, a more compact arrangement of the Amylose spirals takes place in the starch grain and this causes a rise in D.

Table 2

1 Длина волн, мμ	2 Кривая в зависимости от обработки								Амилоса	
	3 очищенный				5 неочищенный					
	контроль		140°C		контроль		140°C		контроль	140°C
	6 диспергирование 24 часа						7 диспергирование 2 часа			
230	0,820	0,700	0,731	0,810	0,685	0,102	0,571	0,520	0,205	0,268
260	0,140	0,385	0,328	0,451	0,362	0,223	0,375	0,370	0,120	0,155
280	0,429	0,355	0,319	0,403	0,328	0,207	0,325	0,316	0,095	0,130
300	0,313	0,286	0,296	0,318	0,275	0,166	0,275	0,250	0,020	0,105
420	0,127	0,108	0,106	0,095	0,092	0,030	0,113	0,036	0,020	0,030
530	0,088	0,076	0,083	0,060	0,063	0,018	0,070	0,008	0,007	0,011
610	0,058	0,062	0,068	0,054	0,047	0,014	0,051	0,004	0,001	0,006

1. Wave Length NM
2. Starch as a Function of the Treatments
3. Purified
4. Control
5. Unpurified
6. Dispersion for 24 hours
7. Dispersion for 2 hours

We obtained and also spectrophotometered complexes of iodine with purified starch and Amylose. Samples of starch and Amylose were dispersed in 1 n NaOH with the addition of iodine as KI. Fifty milligrams of starch and Amylose were dispersed for one hour in 4 milliliters of NaOH. The volume was raised to 15 milliliters. Five milliliters were transferred to 100-milliliter flasks for the starch and 200-milliliter for the Amylose, neutralized with 0.1 HCl to pH 5, one milliliter of Iodine as KI was added (2.5 grams I and 3.75 grams KI in 500 milliliters of distilled water).

The data in Table 3 showed that D is, in the case of the control, larger than in the case of the starch and Amylose that was ripe at 140°C. A decrease in D of the collared complex (Amylose--Iodine) indicate that an Amylose spiral is short in comparison with the controlled Amylose.

TABLE 3

Wave Length NM	Starch		Amylose	
	Depending on the Treatment			
	Control	140°C	Control	140°C
600	0.462	0.459	0.632	0.528
605	0.466	0.460	0.650	0.540
610	0.462	0.455	0.655	0.542
615	0.465	0.460	0.658	0.550
620	0.462	0.452	0.660	0.549
630	0.450	0.445	0.659	0.548
640	0.441	0.438	0.650	0.540

CONCLUSION

During the irradiation and drying of grain at 140°C, processes apparently take place therein which are related with a change in the structure of the starch by its degradation; in particular, with a certain degradation of Amylose.

LITERATURE

1. Oreshko, V. F., Gorin, L. R., Korotchenko, K. A., Maslova, G. M., Chernenko, L. Ye., and Shokhova, I. G., *Izv. vuzov, Pishchevaya tekhnologiya*, No. 5, p. 32, 1962.
2. Korotchenko, K. A., and A.I. Semionov, *Izv. vuzov, Pishchevaya tekhnologiya*, No. 5, p. 26, 1966.
3. Putilova, I. N. and Traubenberg, S. Ye., *Zh. prikl. biokhim. i mikrobiol.*, Vol. 1, No. 5, p. 32, 1965.
4. Pisanskiy, A. N., and N.V. Romenskiy, *Izv. vuzov, Pishchevaya tekhnologiya*, No. 6, p. 49, 1964.
5. Traubenberg, S. Ye., Korotchenko, K. A., and Putilova, I. N., *Izv. vuzov, Pishchevaya tekhnologiya*, No. 6, p. 24, 1965.
6. Masenko, L. V., Romenskiy, N. V., and Yakovenko, V. A., *Izv. vuzov, Pishchevaya tekhnologiya*, No. 4, p. 60, 1967.
7. Ivanov, N. N., *Metody fiziologii i biokhimii rasteniy* (Methods of Physiology and Biochemistry of Plants) 150, Sel'khozgiz, Moscow-Leningrad, 1946.
8. Kerr, R. U., *Khimiya i tekhnologiya krakhmala* (Chemistry and Technology of Starch), Pishchepromizdat, Moscow, 1956.
9. Smirnova-Ikonnikova, M. I., Petrova, T. M., and Mokhnach, V. P., *Dokl. AN SSSR*, No. 2, p. 485, 1961.
10. Knyaginichev, M. I., *Izv. vuzov, Pishchevaya tekhnologiya*, No. 6, p. 35, 1960.
11. Schoch, T. I., *J. Amer. Chem. Soc.*, Vol. 64, p. 2957, 1942. Department of Biochemistry and Grain Science. Manuscript received 5 September, 1967.

UNCLASSIFIED
Security Classification

DOCUMENT CONTROL DATA - R & D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) Foreign Science and Technology Center US Army Materiel Command Department of the Army		2a. REPORT SECURITY CLASSIFICATION Unclassified	
3. REPORT TITLE Alterations in Maize Starch under the Action of Irradiation and Temperature		2b. GROUP	
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Translation			
5. AUTHOR(S) (First name, middle initial, last name) V. A. Yakovenko, N. V. Romenskiy and L. V. Masenko			
6. REPORT DATE 22 April 1969		7a. TOTAL NO. OF PAGES 5	7b. NO. OF REFS N/A
8a. CONTRACT OR GRANT NO. b. PROJECT NO. 9909600 c. 9223628 2301 d. G. Antonelli		9a. ORIGINATOR'S REPORT NUMBER(S) FSTC-HT-23- 745-68 9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report) ACSI Control Number (None)	
10. DISTRIBUTION STATEMENT Each transmittal of this document outside the agencies of the U. S. Government must have the prior approval of the US Army Foreign Science and Technology Center.			
11. SUPPLEMENTARY NOTES The translation rights for this document have not been obtained. This document is not in the public domain.		12. SPONSORING MILITARY ACTIVITY US Army Foreign Science and Technology Center	
13. ABSTRACT During the irradiation and drying of grain at 140°C, processes apparently take place therein which are related with a change in the structure of the starch by its degradation; in particular, with a certain degradation of Amylose. In this study, corn containing 13% moisture was irradiated with γ rays from Co^{60} at doses of 10^5 and $1.5 \cdot 10^6$ R. The starch was then extracted from non-irradiated corn as well. The viscosity ratio was calculated, as well as molecular weight and degree of polymerization.			

DD FORM 1473

REPLACES DD FORM 1473, 1 JAN 64, WHICH IS OBSOLETE FOR ARMY USE.

UNCLASSIFIED
Security Classification

UNCLASSIFIED
Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
ionizing glucoside depolymerization degradative "cross-linking" VIR-42 GUB-800 Pinkevich viscometer Gagedorn-Jensen [7] alkali lability Schoch and Jensen [8] Amylose "blue number" Smirnova-Ikonnikova [9] SF-4A spectrophotometer weighted mean						

UNCLASSIFIED

SUPPLEMENTARY

INFORMATION

NOTICES OF CHANGES IN CLASSIFICATION, DISTRIBUTION AND AVAILABILITY

69-20

15 October 1969

IDENTIFICATION	FORMER STATEMENT	NEW STATEMENT	AUTHORITY
AD-851 744, Army Foreign Science and Technology Center, Washington, D. C. Rept. no. FSTC-HI- 23-745-6 22 Apr 69	AD-851 744, others to Commander, Army Foreign Science and Technology Center, Washington, D. C.	No limitation	USAFSTC ltr, 4 Aug 69

Reproduced From
Best Available Copy